

VITAPAN®
VITAPAN PLUS®
VITA PHYSIODENS®
VITA LINGOFORM

Physical properties*

Property	Unit of measure	Value
Flexural strength	MPa	80
Elastic Modulus	MPa	4350
Impact Strength	kJ/m ²	4,3
Vickers Hardness (HV 0,5/30)	MPa	275
Glass Transition Temperature	°C	118
Abrasion Resistance (Pin-on-Block) Depth Volume	 μm μm ³	 -135 -15

*The given physical and technical values are typical values and apply to testing samples manufactured on our premises and in-house measuring equipment.
 If samples manufactured elsewhere and/or other measuring instruments are used, differing results are to be expected.

The requirements of ISO 22112 are fulfilled.

VITAPAN®, **VITAPAN PLUS®**, **VITA PHYSIODENS®** and **VITA LINGOFORM** are certified and bear the CE mark **CE** 0124.

